

## PRODUCT DATA SHEET

**PRODUCT:** EASTTO RUBBER EXTENDER OILS

**GRADE:** Light, Medium, Heavy, Extra Heavy

**DESCRIPTION:** EASTTO RUBBER EXTENDER OILS Light, Medium, Heavy and Extra heavy are high aromatic type oils and produced during the solvent extraction for the production of lubricating base oils at the Refinery. These are dark coloured oils and have good solvency for which they are compatible with most of the rubber polymers.

**APPLICATION:** EASTTO RUBBER EXTENDER OILS Light, Medium, Heavy and Extra heavy are used in the manufacture of automobile tyres, thread rubber, belting, battery cases, rubber bushes and other dark coloured rubber goods etc. where colour is not an important factor



Natural and synthetic rubber, Particularly for the manufacturing of automotive rubber tubes

### TYPICAL PROPERTIES:

CHARACTERISTICS	EASTTO RUBBER EXTENDER OIL LIGHT	EASTTO RUBBER EXTENDER OIL MEDIUM	EASTTO RUBBER EXTENDER OIL HEAVY	EASTTO RUBBER EXTENDER OIL EXTRA HEAVY
Kinematic Viscosity at 100°C, cst	18 - 21	21 - 26	26 - 30	30 - 40
Flash Point °C	220	220	220	220
Aniline Point, °C	52	50	48	45

**PACKING:** 210 Litres Drum

**Date of issue:** 05.10.2009

**Date of revision:** 01.03.2017

**1<sup>st</sup> Revision:** 29.05.2019 (CK)

**PDS No.** 07.05.05 – 07.05.08

These Characteristics are typical of current production while future production will confirm to **EASTERN PETROLEUM PVT. LTD.** Specification variation in these characteristics may occur.



## PRODUCT DATA SHEET

**PRODUCT:** **EASTTO RUBBER PROCESS 32, 68**

**DESCRIPTION:** **EASTTO RUBBER PROCESS 32, 68** are medium viscosity rubber process oils blended from highly refined solvent extracted base stocks with lowsulphur content and suitable for use as plasticizers.

**APPLICATION:** **EASTTO RUBPROCESS 32, 68** are recommended for the manufacture of various rubber products from both natural and synthetic rubber, particularly for the manufacturing of automotive rubber tubes.



Natural and synthetic rubber, Particularly for the manufacturing of automotive rubber tubes

### TYPICAL PROPERTIES:

CHARACTERISTICS	EASTTO RUBPROCESS 32	EASTTO RUBPROCESS 68
ASTM Colour	2	4
Kinematic Viscosity at 40°C, cst	32	68
Flash Point °C	190	200
Aniline Point, °C	97	98

**PACKING:**210Litres Drum

**Date of issue:** 10.11.2014

**Date of revision:** 16.08.2016

**1<sup>st</sup> Revision:** 29.05.2019 (CK)

These Characteristics are typical of current production while future production will confirm to **EASTERN PETROLEUM PVT. LTD.** Specification variation in these characteristics may occur.

